

Data Sheet

Select Series

of Solid Vinyl Siding



Illustration	Description/Packaging	Colors/Color Nos.	* Premium colors are made with Armor Coat UVA™
<p>21SS24 __ __</p>	<p>Double 4" Siding Panel Matte Finish Length 12' 6" 24 Panels/Carton 2 Sq./Carton Carton Weight: 91 lbs.</p>	<p>White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22)</p>	<p>Summer Wheat (26) Harbor Stone (44) *Vintage Sage (55) *Adobe Clay (60)</p>

NOTE: Non-stocking item, 100 minimum carton order, per color, per profile

Illustration	Description/Packaging	Colors/Color Nos.	* Premium colors are made with Armor Coat UVA™
<p>21SS65BD __ __</p>	<p>6.5" Beaded Siding Panel Matte Finish Length 12' 4" 30 Panels/Carton 2 Sq./Carton Carton Weight: 97 lbs.</p>	<p>White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22)</p>	<p>Summer Wheat (26) Harbor Stone (44) *Vintage Sage (55) *Adobe Clay (60)</p>

Illustration	Description/Packaging	Colors/Color Nos.	* Premium colors are made with Armor Coat UVA™
<p>21BB70 __ __</p>	<p>Board & Batten Siding Panel Carrington Finish Length 10' 17 Panels/Carton 1 Sq./Carton Carton Weight: 53 lbs.</p>	<p>White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22)</p>	<p>Summer Wheat (26) Harbor Stone (44) *Vintage Sage (55) *Adobe Clay (60)</p>

Illustration	Description/Packaging	Colors/Color Nos.	* Premium colors are made with Armor Coat UVA™
<p>21SS333 __ __</p>	<p>Triple 3" Siding Panel Matte Finish Length 12' 20 Panels/Carton 2 Sq./Carton Carton Weight: 73.30 lbs.</p>	<p>White Birch (02) Classic Sand (11) Warm Sandalwood (17) Sunny Maize (22)</p>	<p>Summer Wheat (26) Harbor Stone (44) *Vintage Sage (55) *Adobe Clay (60)</p>

NOTE: Non-stocking item, 100 minimum carton order, per color, per profile

Select Series Solid Vinyl Siding

Styles to fit your most exacting need.



Style Crest, Inc. 2450 Enterprise Street
Drawer A
Fremont, OH 43420

Product Test Data

Siding Thickness.....0.044" ± .001"
Board & Batten Thickness.....0.048" ± .001"
Specific Gravity.....1.45
Tensile Strength (PSI).....7,154
Tensile Modulus (PSI).....416,900
IZOD Impact Strength @ 32°F.....Passes per ASTM D3679
Heat Deflection Temp. @ 264 PSI.....169°F
Coefficient of Linear Expansion..... 3.30×10^{-5}
Weight.....47 lbs. per square
Warpage.....0.00"
Heat Shrinkage.....0.3%

Impact Resistance.....Passes per ASTM D3679
Surface Distortion @ 140°F.....0
Fire Rating.....Class A
Flame Spread Index.....10
Smoke Developed.....395
Fuel Contribution.....0
Average Time Of Burning.....Self extinguished
Average Extent Of Burning.....2.379mm
Weathering.....Passes per ASTM D3679
Windload Rating*162 MPH
**(Wind Velocity based on IBC)*

Select Series Vinyl Siding passes or exceeds all industry standards per ASTM D3679.

Made in the U.S.A. by America's dedicated workforce.
Specifications subject to change without notice.

